

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

In the Claims:

Claim 1 (Currently Amended). A synthetic resin-impregnated body, comprising:

a primary product formed of an expanded or at least partially recompressed expanded graphite having a liquid-accessible open pore system;

said ~~graphite containing~~ primary product being impregnated with at least one of:

at least one solvent-free, ~~low viscosity, storage stable,~~ polymerizable acrylic resin system; and

polymers obtained by curing said at least one resin system.

Claim 2 (Original). The synthetic resin-impregnated body according to claim 1, wherein said at least one acrylic resin system contains triethyleneglycol dimethacrylate and at least one initiator system.

Claim 3 (Original). The synthetic resin-impregnated body according to claim 2, wherein said at least one acrylic resin system contains azo initiators as said at least one initiator.

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

Claim 4 (Original). The synthetic resin-impregnated body according to claim 3, wherein said azo initiators contained in said at least one acrylic resin system are selected from the group consisting of 2,2'-dimethyl-2,2'-azodipropionitrile, 1,1'-azobis(1-cyclohexanecarbonitrile) and azoisobutyric acid dinitrile.

Claim 5 (Original). The synthetic resin-impregnated body according to claim 1, wherein said at least one acrylic resin system has a storage stability at room temperature of more than two days.

Claim 6 (Original). The synthetic resin-impregnated body according to claim 1, wherein said at least one acrylic resin system has a storage stability at room temperature of more than two weeks.

Claim 7 (Original). The synthetic resin-impregnated body according to claim 1, including up to 50% by weight of acrylic resin.

Claim 8 (Original). The synthetic resin-impregnated body according to claim 1, including 5 to 25% by weight of acrylic resin.

Appl. No. 10/006,419.

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

Claim 9 (Original). The synthetic resin-impregnated body according to claim 1, including 10 to 20% by weight of acrylic resin.

Claim 10 (Currently Amended). ~~The A~~ synthetic resin-impregnated body ~~according to claim 1, wherein a~~, comprising:

a primary product formed of an expanded or at least partially recompressed expanded graphite having a liquid-accessible open pore system, said primary product contains containing fillers selected from the group consisting of ceramic fillers, mineral fillers, electrically non-conductive fillers, and electrically conductive fillers;

said primary product being impregnated with at least one of:

at least one solvent-free polymerizable acrylic resin system; and

polymers obtained by curing said at least one resin system.

Claim 11 (Currently Amended). The synthetic resin-impregnated body according to claim 1, including at least two independently held together networks, one of said networks being formed of a connected framework made of expanded or

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

expanded and thereafter at least partially recompressed graphite ~~with good electrical conductivity as well as good thermal conductivity~~ that is thermally conductive and has an electrical volume resistance from 0.10 to 0.77 m Ω , and the other of said networks being a connected network made of synthetic material having penetrated into said graphite.

Claim 12 (Currently Amended). The synthetic resin-impregnated body according to claim 1, including a surface, regions close to said surface, and ~~another~~ a remaining part, said at least one acrylic resin system disposed only in one of said remaining part and said regions.

Claim 13 (Original). The synthetic resin-impregnated body according to claim 1, wherein a continuous resin surface film is not present and the body is electrically conductively contactable.

Claim 14 (Currently Amended). A process for producing a body containing at least one synthetic resin, which comprises:

providing a primary product ~~made~~ formed of expanded or at least partially recompressed expanded graphite ~~with an open~~ having a liquid-accessible pore system;

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

impregnating the primary product with at least one solvent-free, ~~low-viscosity, storage-stable,~~ polymerizable acrylic resin system to form a resin-containing, uncured intermediate product; and

finally subjecting the resin-containing, uncured intermediate product to a curing treatment for the at least one resin system.

Claim 15 (Original). The process for producing a body containing at least one synthetic resin according to claim 14, which further comprises processing the resin-containing, uncured intermediate product to form a shaped body; and carrying out the subjecting step by subjecting the uncured shaped body produced from the uncured intermediate product to a curing treatment for the at least one resin system.

Claim 16 (Original). The process for producing a body containing at least one synthetic resin according to claim 15, which further comprises simultaneously shaping the acrylic resin-containing body and curing the resin system that is present as a result of temperature impact.

Appl. No. 10/006,413

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

Claim 17 (Currently Amended). The A process for producing a body containing at least one synthetic resin ~~according to claim 16~~, which further comprises:

providing a primary product formed of expanded or at least partially recompressed expanded graphite having a liquid-accessible pore system;

providing limiting an ash value to not more than for percent of the primary product made of expanded or at least partially recompressed expanded graphite having an open pore system, with an ash value of not more than four per cent;

impregnating the primary product with at least one solvent-free polymerizable acrylic resin system to form a resin-containing, uncured intermediate product;

processing the resin-containing, uncured intermediate product to form a shaped body;

finally subjecting the resin-containing, uncured intermediate product to a curing treatment for the at least one resin system;

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

carrying out the subjecting step by subjecting the uncured shaped body produced from the uncured intermediate product to a curing treatment for the at least one resin system; and

simultaneously shaping the acrylic resin-containing body and curing the resin system that is present as a result of temperature impact.

Claim 18 (Currently amended). The A process for producing a body containing at least one synthetic resin ~~according to claim 16~~, which ~~further~~ comprises:

providing a primary product formed of expanded or at least partially recompressed expanded graphite having a liquid-accessible pore system;

providing limiting an ash value to not more than two percent of the primary product made of expanded or at least partially recompressed expanded graphite having an open pore system;
~~with an ash value of not more than two per cent;~~

impregnating the primary product with at least one solvent-free polymerizable acrylic resin system to form a resin-containing, uncured intermediate product;

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

processing the resin-containing, uncured intermediate product to form a shaped body;

finally subjecting the resin-containing, uncured intermediate product to a curing treatment for the at least one resin system;

carrying out the subjecting step by subjecting the uncured shaped body produced from the uncured intermediate product to a curing treatment for the at least one resin system; and

simultaneously shaping the acrylic resin-containing body and curing the resin system that is present as a result of temperature impact.

Claim 19 (Currently Amended). The process for producing a body containing at least one synthetic resin according to claim 14, which further comprises ~~providing~~ maintaining a bulk density in a range of from 0.1 to 1.8 g/cm³ of the primary product made of expanded or at least partially recompressed expanded graphite having an open pore system, with a bulk density in a range of from 0.1 to 1.8 g/cm³.

Claim 20 (Currently Amended). The process for producing a body containing at least one synthetic resin according to claim 14, which further comprises ~~providing~~ maintaining a bulk

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

density in a range of from 0.3 to 1.5 g/cm³ of the primary
product made of expanded or at least partially recompressed
expanded graphite having an open pore system, ~~with a bulk~~
~~density in a range of from 0.3 to 1.5 g/cm³.~~

Claim 21 (Currently Amended). The process for producing a
body containing at least one synthetic resin according to
claim 14, which further comprises ~~providing~~ maintaining a bulk
density in a range of from 0.5 to 1.3 g/cm³ of the primary
product made of expanded or at least partially recompressed
expanded graphite having an open pore system, ~~with a bulk~~
~~density in a range of from 0.5 to 1.3 g/cm³.~~

Claim 22 (Currently Amended). The process for producing a
body containing at least one synthetic resin according to
claim 14, ~~which further comprises carrying out~~ wherein the
step of impregnating the primary product made of expanded or
at least partially recompressed expanded graphite having an
open pore system, is performed with acrylic resins having a
viscosity at room temperature of less than 100 mPa.s.

Claim 23 (Currently Amended). The process for producing a
body containing at least one synthetic resin according to
claim 14, ~~which further comprises carrying out~~ wherein the
step of impregnating the primary product made of expanded or
at least partially recompressed expanded graphite having an

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

open pore system ~~is performed~~ with acrylic resins having a viscosity at room temperature of less than 50 mPa.s.

Claim 24 (Currently Amended). The process for producing a body containing at least one synthetic resin according to claim 14, ~~which further comprises carrying out~~ wherein the step of impregnating the primary product made of expanded or at least partially recompressed expanded graphite having an open pore system ~~is performed~~ with acrylic resins having a viscosity at room temperature of less than 20 mPa.s.

Claim 25 (Original). The process for producing a body containing at least one synthetic resin according to claim 14, wherein the primary product made of expanded or at least partially recompressed expanded graphite having an open pore system, takes-up up to 100% by weight of its own weight of acrylic resins, during the impregnating step.

Claim 26 (Original). The process for producing a body containing at least one synthetic resin according to claim 14, wherein the primary product made of expanded or at least partially recompressed expanded graphite having an open pore system, takes-up 5 to 35% by weight of its own weight of acrylic resins, during the impregnating step.

Appl. No. 10/006,411

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

Claim 27 (Original). The process for producing a body containing at least one synthetic resin according to claim 14, wherein the primary product made of expanded or at least partially recompressed expanded graphite having an open pore system, takes-up 10 to 25% by weight of its own weight of acrylic resins, during the impregnating step.

Claim 28 (Currently Amended). The process for producing a body containing at least one synthetic resin according to claim 14, ~~which further comprises carrying out~~ wherein the step of curing the acrylic resins is performed in less than ten minutes under the effect of temperatures of up to 200°C.

Claim 29 (Currently Amended). The process for producing a body containing at least one synthetic resin according to claim 14, ~~which further comprises carrying out~~ wherein the step of curing the acrylic resins is performed in less than three minutes under the effect of temperatures of up to 200°C.

Claim 30 (Currently Amended). ~~The A~~ A process for producing a body containing at least one synthetic resin ~~according to claim 14~~, which ~~further~~ comprises:

providing a primary product formed of expanded or at least partially recompressed expanded graphite having a liquid-accessible pore system;

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

mixing the expanded graphite with fillers selected from the group consisting of ceramic fillers, mineral fillers, electrically non-conductive fillers and electrically conductive fillers;

processing the mixed expanded graphite to form a filler-containing primary product; and

then impregnating the primary product with ~~resin~~ at least one solvent-free polymerizable acrylic resin system to form a resin-containing, uncured intermediate product; and

finally subjecting the resin-containing, uncured intermediate product to a curing treatment for the at least one resin system.

Claim 31 (Currently Amended). A sealing element, comprising:

a synthetic resin-impregnated body having a primary product formed of an expanded or at least partially recompressed expanded graphite and having a liquid-accessible pore system; said graphite ~~containing~~ being impregnated with at least one of:

at least one solvent-free, ~~low viscosity, storage stable,~~ polymerizable acrylic resin system; and

Appi. No. 12/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

polymers obtained by curing said at least one resin system.

Claim 32 (Currently Amended). A fuel cell component, comprising:

a synthetic resin-impregnated body having formed of an expanded or at least partially recompressed expanded graphite having a liquid-accessible pore system; said graphite containing being impregnated with at least one of:

at least one solvent-free, ~~low-viscosity, storage stable,~~ polymerizable acrylic resin system; and

polymers obtained by curing said at least one resin system.

Claim 33 (Currently Amended). A heat-conducting element, comprising:

a synthetic resin-impregnated body having a primary product having formed of an expanded or at least partially recompressed expanded graphite having a liquid-accessible open pore system; said graphite containing being impregnated with at least one of:

Appl. No. 10/006,419

Amendment Dated July 15, 2004

Reply to Office Action of March 15, 2004

at least one solvent-free, ~~low viscosity, storage stable,~~
polymerizable acrylic resin system; and

polymers obtained by curing said at least one resin
system.

Claim 34 (New). The sealing element according to claim 31,
having a gas permeability from 0.001 to 0.016 mg/m².s.

Claim 35 (New). A fuel cell using oxygen as an oxidant,
comprising the fuel cell component according to claim 32.